



HITEX INSULATION (NINGBO) CO., LTD

Room2004,2nd Block, Shangdong Business Centre, Ningbo,315041

Tel:+86-574-27898220,Fax:+86-574-27898230

Technical Data Sheet

1	WEAVE		PLAIN	TEST METHOD
2	YARN TEX	WARP	CT 11 1000	ISO 4602
		WEFT	CT 11 1000	
3	WIDTH		100cm	DIN EN 1773
4	CLOTH WEIGHT		1000±20 g/m ²	DIN EN 12127
5	COLOR		WHITE, TEXTURIZED	
6	TOTAL THICKNESS		1.5±0.2m	DIN EN ISO 5084
7	THREAD COUNT	WARP	6.2 per cm	DIN EN 1049-2
		WEFT	3.0 per cm	DIN EN 1049-2
8	TENSILE STRENGTH MIN	WARP	4000 N/50mm	EN ISO 13934-1
		WEFT	3000 N/50mm	EN ISO 13934-1
9	TEMPERATURE RESISTANT		BASIC FABRIC SHORT TERM	550°C 600°C