

## Technical Datasheet - METYX Composite Reinforcements

<b>PRODUCT CODE</b>	5200.006.185
<b>PRODUCT NAME</b>	CX400 E050-45/45 BIAxIAL CARBON-127CM
<b>PRODUCT DESCRIPTION</b>	.
<b>CUSTOMER CODE</b>	.
<b>CUSTOMER ID</b>	.

REINFORCEMENT CONSTRUCTION		
LAYER	FIBER TYPE	AREA WEIGHT
1	+45° 800 Tex - 12K Carbon	201 gr / m2
2	0° 68 Tex	1 gr / m2
3	-45° 800 Tex - 12K Carbon	201 gr / m2
4	Stitch 76 Dtex	5 gr / m2
5		
6		
7		

\* Checked via own test based on ISO 3374.

**TOTAL\*** 408 gr / m2 (± %5)

OTHER PROPERTIES		ROLL INFO	
Stitch Gauge	5 stitches/inch	Roll Width	127 cm
Stitch Type	Piilar	Roll Weight	26 kg
Stitch Length	3 mm	Roll Length	50 m
Pilot Yarn / Position	--- / ---	Core Diameter	76 mm

Resin Compatibility	Loss on Ignition	Moisture Content
-	-	-

<b>Packaging</b>	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.
<b>Labelling</b>	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.
<b>Storage</b>	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.

Certification	DNV	Lloyd's Register
Metyx products are produced by Tlateks A.S. company who is run by ISO 9001:2008 QA System.	TYPE Approved	TYPE Approved

**Note:** The above specifications reflect the product data on release date but are subject to change without prior notice.

**Address:**  
H-7400 Kaposvár, Dombóvári út  
3657/126. hrsz. Hungary