

Hollow Glass Sphere Catalog

Type	Specific Gravity (g/cm ³)	Bulk Density (g/cm ³)	Crush Stength (Mpa/PSI)	Moisture %	Flotation %	Particle Size		
						D10	D50	D90
HK20	0.18-0.22	0.10-0.13	3.50/500	0.5	92	30	65	120
HK25	0.23-0.27	0.12-0.14	5.17/750	0.5	92	25	65	100
HK30	0.28-0.32	0.14-0.16	10.34/1500	0.5	92	25	65	95
HK37	0.35-0.40	0.18-0.22	20.67/3000	0.5	92	20	55	90
HK40	0.38-0.42	0.20-0.23	27.56/4000	0.5	92	20	55	90
HK46	0.44-0.48	0.24-0.27	41.34/6000	0.5	92	20	55	90
HK55	0.53-0.57	0.30-0.33	68.96/10000	0.5	92	20	55	90
HK60	0.58-0.62	0.34-0.37	82.76/12000	0.5	92	20	50	90
HL22	0.19-0.25	0.11-0.16	3.50/500	0.5	92	25	65	120
HL25	0.23-0.27	0.12-0.14	5.17/750	0.5	92	25	65	100
HL30	0.28-0.32	0.14-0.16	10.34/1500	0.5	92	25	65	95
HL35	0.33-0.37	0.17-0.19	20.67/3000	0.5	92	20	60	90
HL40	0.38-0.42	0.20-0.23	27.56/4000	0.5	92	20	55	90
HL46	0.44-0.48	0.24-0.27	41.34/6000	0.5	92	20	55	90
HL55	0.53-0.57	0.30-0.33	68.96/8000	0.5	92	20	55	90
HL60	0.58-0.62	0.34-0.37	68.96/10000	0.5	92	20	55	90
HR32	0.30-0.35	0.15-0.18	13.79/2000	0.5	92	25	65	90
HR55	0.53-0.57	0.30-0.33	68.96/10000	0.5	92	20	55	90
HR60	0.58-0.62	0.34-0.37	82.76/12000	0.5	92	20	50	90
HS60	0.58-0.63	0.34-0.37	124.14/18000	0.5	92	20	50	85