

Technical Datasheet - METYX Composite Reinforcements

PRODUCT CODE	5200.004.004		
PRODUCT NAME	Q1200E10A-0/45/90/45 QUADRIAXIAL E GLASS-127CM		
PRODUCT DESCRIPTION			
CUSTOMER CODE			
CUSTOMER ID	•		

REINFORCEMENT CONSTRUCTION					
	LAYER	FIBER TYPE	AREA WEIGHT		
1	0°	600 Tex	283 gr / m2		
2	+45°	300+600 Tex	300 gr / m2		
3	90°	600 Tex	307 gr / m2		
4	-45°	300+600 Tex	300 gr / m2		
5	Stitch	76 Dtex	10 gr / m2		
6					
7					

* Checked via own test based on ISO 3374.

TOTAL* 1200 gr / m2 (±%3)

OTHER PROPERTIES			ROLL INFO	
Stitch Gauge	10 stitches/inch	Roll Width	127 cm	
Stitch Type	Pillar-Tricot	Roll Weight	68 kg	
Stitch Length	3 mm	Roll Length	45 m	
Pilot Yarn / Position	/	Core Diameter	76 mm	

Resin Compatibility		Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins		Max.%0,70 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)
Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.		
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.		
Storage	Store at %40-70 relative humidity and 18-30 ^o C temperature range. Recommended to be brought to working area 24 hrs prior to use.		

Certification	DNV	Lloyd's Register
Metyx products are produced by Telateks A.S. company	TYPE Approved	TYPE Approved
who is run by ISO 9001:2008 QA System.		

Note: The above specifications reflect the product data on release date but are subject to change without prior notice.

Address:

Orhanli Beldesi 34956 Tuzla Istanbul – TURKIYE



 Phone:
 +90-216-394-32-60

 Fax
 :
 +90-216-394-32-58

 Web
 :
 www.metyx.com