



湖北汇尔杰新材料科技股份有限公司

HUBEI HUIERJIE NEW MATERIAL TECHNOLOGY CO.,LTD

地址:中国湖北省襄阳市人民西路 19 号

ADD:NO.19 West Renmin Road Xiangyang City Hubei, China

电话(Tele)+86(0710)3120933 传真(Fax)+86(0710)3121777 邮编 (Postcode) 441002

网址(Website): WWW.AR-glassfibre.com

E-mail: fred@ar-glassfibre.com

Product Information: ARG SPRAY ROVING

ARC 13- 2700H ZRO₂≥16.7%

Technical Date Sheet

Test Condition: Temperature & Humidity 24°C 56%

Material properties: 1、 material			AR-glassfibre
2、 ZrO ₂	%		≥16.7
3、 Filament dia	um		13±2
4、 Liner weight of Roving	Tex		2700±270
5、 Specific gravity	g/cm ³		2.7

Technical Data:			
1、 Colour	/		white
2、 Moisture content	%		≤0.2
3、 Size content	%		1.8
4、 Breaking strength	N/tex		0.42
5、 Softning temperature	°C		860
6、 Elastic modulus	GN/m ²		82
7、 Stiffness	mm		≥120
8、 Fire resistance	Incombustible		
	Inorganic material		

Noted: HEJ ARG FIBER MIN 16.7%, reach the EU BSEN 15422:2008 AND USA ASTM C 1666 STANDARD