

## **Technical Datasheet - METYX Composite Reinforcements**

PRODUCT CODE	5200.002.059	
PRODUCT NAME	X300E05A-45/45 BIAXIAL E GLASS FABRIC-127CM	
PRODUCT DESCRIPTION		
CUSTOMER CODE		
CUSTOMER ID	•	

		REINFORCEMENT CONSTRU	CTION
	LAYER	FIBER TYPE	AREA WEIGHT
1	+45°	300 Tex	150 gr / m2
2	0°	68 Tex	1 gr / m2
3	-45°	300 Tex	150 gr / m2
4	Stitch	76 Dtex	5 gr / m2
5			
6			
7			

\* Checked via own test based on ISO 3374.

TOTAL\* 306 gr / m2 (±%3)

OTHER PROPERTIES		I	ROLL INFO	
Stitch Gauge	5 stitches/inch	Roll Width	127 cm	
Stitch Type	Pillar	Roll Weight	66 kg	
Stitch Length	3 mm	Roll Length	170 m	
Pilot Yarn / Position	/	Core Diameter	76 mm	

Resin Compatibilit	y	Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins		Max.%0,70 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)
Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.		
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.		
Storage	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.		

Certification	DNV	Lloyd's Register
Metyx products are produced by Telateks A.S. company	TYPE Approved	
who is run by ISO 9001:2008 QA System.		

Note: The above specifications reflect the product data on release date but are subject to change without prior notice.

Address:

Orhanli Beldesi 34956 Tuzla Istanbul – TURKIYE



 Phone:
 +90-216-394-32-60

 Fax
 :
 +90-216-394-32-58

 Web
 :
 www.metyx.com