



Taiwan Glass Ind. Corp.

Flat Glass • Container Glass • Tableware Glass • Fiber Glass

P. O. Box 81-700, Taipei, Taiwan

Tel: 2-2713-0333 Taipei

Fax: 2-2715-0333 ,2-2718-0711

SPECIFICATION OF DIRECT ROVING TGFR 442-2400 TEX

ITEM	SPECIFICATION
GLASS TYPE	E-GLASS
BINDER NO.	442
COUPLING AGENT	SILANE
TEX g/1000M	2400 ± 240
MOISTURE %	< 0.06
SOLIDS %	0.65 ± 0.20
FILAMENT DIAMETER μ m	17 ± 1.4
ALKALI CONTENT %	< 0.80
APPEARANCE	GOOD
COMPATIBLE RESIN	PP
PROCESS	LFT

UPDATE : 2015-07-23

STORAGE CONDITIONS

- *It is recommended to store glass fibre products in a cool dry area. Temperature should not exceed 35°C and the relative humidity should be kept below 75 %.
- *Glass fibre products must remain in packaging material until just prior to its use.
- *Validity : We recommend this product should be used within 12 months from the delivery date to ensure optimum performance.
- *Do not stack pallets higher than two.

Kuo, M. C.
Q/A Manager